

exena.

FASTER S3 S FO SR ESD



DESCRIPTION	NORM EN ISO 20345:2022	RESULT	REQUIREMENT
UPPER: Breathable fabric	5.4.3 Tear strength	92,2 N	≥60 N
	5.4.6 Water vapor permeability	6,5 mg/cm ² h	≥ 0,8 mg/cm ² h
	Coefficient	61,0 mg/cm ²	≥ 15,0 mg/cm ²
LINING OF TONGUE: Breathable, abrasion resistance.	5.5.2 Tear strength	65,8 N	≥ 15 N
	5.5.3 Abrasion resistance (Wet)	No holes	25.600 cycles
	Abrasion resistance (Dry)	No holes	51.200 cycles
QUARTER LINING: Breathable, abrasion resistance.	5.5.2 Tear strength	42,4 N	≥ 15 N
	5.5.3 Abrasion resistance (Wet)	No holes	25.600 cycles
	Abrasion resistance (Dry)	No holes	51.200 cycles
COUNTER LINING: Breathable, abrasion resistance.	5.5.2 Tear strength	21,6 N	≥ 15 N
	5.5.3 Abrasion resistance (Wet)	No holes	25.600 cycles
	Abrasion resistance (Dry)	No holes	51.200 cycles
SAFETY TOE CAP: Aluminum	5.3.2.6 Impact resistance	17,5 mm	≥ 14 mm
	5.3.2.7 Compression resistance	20,5 mm	≥ 14 mm
PIERCE-RESISTANCE: Textile pierce proof footbed,	6.2.1.1.3 Resistance to perforation	1285 N	≥ 1100 N

EXENA SRL
via Breda 20
62012 Civitanova M. MC
ITALY

REA MC144207
Reg. Impr. Trib. MC 01336080435
C.F. e P. IVA 01336080435
Cap. Soc. € 25.823,00 i.v.

+39 0733 89 72 56
info@exena.com
amministrazione@pec.exena.it

exena.com

exena.

FOOTBED: Removable, cushioned, antistatic insole.

OUTSOLE: EVA, Antislip sole, SR

5.7.4.2 Abrasion resistance (Dry)
Abrasion resistance (Wet)

5.8.3 Tear strength
5.8.4 Abrasion resistance
5.8.5 Flexing resistance
6.4.2 Oils resistance
6.2.10 Slip resistance on ceramic with glycerin
(tilted towards the heel of 7°)
(tilted towards the tip of 7°)
5.3.5.2 Slip resistance on ceramic with cleaning agent
(tilted towards the heel of 7°)
(tilted towards the tip of 7°)
6.2.2.2 Antistatic

No holes
No holes

23,2 kN/m
96,4 mm³
0,5 mm
7,4 %

0,30
0,29

0,42
0,39

Dry: 96,0 MΩ
Wet: 11,9 MΩ

25.600 cycles
12.800 cycles

≥ 5 kN/m
≤ 250 mm³
≤ 4,0 mm
≤ 12%

≥ 0,19
≥ 0,22

≥ 0,31
≥ 0,36

0,1 ÷ 1000 MΩ
0,1 ÷ 1000 MΩ

SIZES: 36-48

WEIGHT: (KG)

36 37 38 39 40 41 42 43 44 45 46 47 48

0.802 0.848 0.894 0.940 0.986 1.032 1.078 1.124 1.170 1.216 1.262 1.308 1.354